

**LUXOL A/S**Tangrimme 19, Kløv Kær  
DK - 7700 ThistedTel. +45 97 99 51 66  
www.luxol.dk  
luxol@luxol.dk  
CVR/VAT: DK 29 42 43 73**Product Data Sheet**

05.09.2024

**Product: Luxovit 5-8 mm****Description:**

Luxovit is calcined flint. Calcined means that the raw flint has been heated up to 1100 degrees C. and this treatment makes the dark blue flint almost white. The product can be delivered either in small 25 kg plastic bags on pallets or in big bags on pallets.

**TYPICAL CHEMICAL ANALYSIS:**

SiO <sub>2</sub>	97,0%
Na <sub>2</sub> O	0,3%
K <sub>2</sub> O	0,3%
MgO	0,3%
CaO	1,1%
Fe <sub>2</sub> O <sub>3</sub>	0,2%
Al <sub>2</sub> O <sub>3</sub>	0,6%

**GRADING:**

Above 8.0 mm	max 10%
Below 5.6 mm	max 15%



Luxovit: -

Supplied to:

Against purchase order:

has been tested and complies with our specifications.

Cont. no.:

Seal no.:

**Lot content spec.**

No.	Packaging	From week/year	Weight in kg	Weight in total
-	-	-	-	0
-	-	-	-	0
-	-	-	-	0
-	-	-	-	0
-	-	-	-	0